



Texture Plus®  
EXTRAORDINARILY REALISTIC

www.textureplus.com

## ▶ Solvent Resistance

—TEST NO. TP06—

### I. Scope

This test procedure tests the solvent resistance of the paint/polymer system, particularly when overreduced solvent based top coats are used over the Texture Plus® system.

### II. Materials and Equipment

- a. VM&P Naphtha.
- b. Xylene.
- c. Texture Plus® production coated parts with barrier coat and top coat.
- d. Kleenex or towel.

### III. Procedure

- a. Age finished parts for 1 week at room temperature (77 degrees F)
- b. Using a Kleenex or towel, dip into either solvent type.
- c. Immediately after dipping into solvent, rub prepared test part with Kleenex or towel firmly. Rub in a 1" back and forth motion. Each back and forth motion counts as one double rub.
- d. Rub panel 25 times.

### IV. Report

- a. Report any loss of coating on surface at number of rubs point.
- b. Compare test results to Texture Plus® standard parts.

### V. Results

- a. The parts tested passed. There was no loss of coating on the Texture Plus® samples tested.

#### Contact Us

Texture Plus®  
1611 Lakeland Avenue  
Bohemia, NY 11716

info@textureplus.com